

Name of The Product : 30x120x2 Nebraska Series Rec.
Production Facility : Glazed Porcelain Factory
Product Group : Dry-pressed ceramic tiles / Group Bla / GL
Recommended Use : Interior & exterior floor
General Properties : Mat
Report Date : 22.11.2024

Test Title	Test Results	Requirements	Decision
Length & Width (mm)	297 x 1195 mm	296,5 – 297,5 mm 1194,5 – 1195,5 mm	OK
Thickness (mm)	20,00 mm	19,7 – 20,3 mm	OK
Straightness of Sides (%)	± % 0,3	± % 0,5	OK
Rectangularity (%)	± % 0,3	± % 0,6	OK
Edge Curvature (%)	± % 0,3	± % 0,5	OK
Corner Curvature (%)	± % 0,3	± % 0,5	OK
Center Curvature (%)	± % 0,3	± % 0,5	OK
Small Colour Differences	First Quality	> %95 perfect	OK
Water Absorption	< 0,1 %	≤ 0,5 %	OK
Breaking Strength (N)	> 9500 N	> 9500 N	OK
Modulus of Rupture (N/mm²)	>55 N/mm²	> 35 N/mm²	OK
Abrasion Resistance (PEI)	Mable:III Elm:IV Oak:III	As declared	OK
Coeff. Of Thermal Expansion	< 7,0 x 10⁻⁶	As declared	OK
Thermal Shock Resistance	Resistant	Required	OK
Crazing Resistance	Resistant	Required	OK
Frost Resistance	Resistant	Required	OK
Coefficient of Friction (μ)	~0,62	As declared	OK
Moisture Expansion (mm/m)	< 0,3	As declared	OK
Impact Resistance	Resistant	As declared	OK
Staining Resistance	Class 5	Min. Class 3	OK
Resistance to low conc. of Acid & Alkalies	A	As declared	OK
Resistance to high conc. of Acid & Alkalies	A	As declared	OK
Household Chemicals	A	Min. B	OK
Release of Cadmium	< 0,07 mg/dm²	As declared	OK
Release of Lead	< 0,8 mg/dm²	As declared	OK
OVERALL RESULT	All test results are positive according to the norms of ISO 13006 and EN 14411 standards, Annex G.		

Prepared by

Mustafa Oztürk
Quality Assurance Specialist



Approved by

Ahmet Pehlivan
Quality Assurance Manager

